# 13

# TXTURE comfortBack$^{eco}$

| | |
|---|---|
| CONSTRUCTION<br>STRUCTURE<br>STRUKTUR<br>STRUCTUUR | Tufted 1/12” Loop Tip Sheared<br>Tufté 1/12” Bouclé Tip Sheared<br>Getuftet 1/12” Schlinge Tip Sheared<br>Getuft 1/12” Luspool Tip Sheared |
| PILE MATERIAL<br>COUCHE D’USURE<br>POLMATERIAL<br>POOLMATERIAAL | 100% ECONYL® yarn<br>100% Regenerated Solution Dyed Nylon |
| SECONDARY BACKING<br>DOSSIER<br>RÜCKENAUSSTATTUNG<br>RUG | comfortBack$^{eco}$: shock absorbing and noise reducing carpet tile backing enhanced with a fully recyclable polyolefin based layer made from minimum 70% post-industrial recycled content |
| TOTAL WEIGHT<br>POIDS TOTAL<br>GESAMTGEWICHT<br>TOTAAL GEWICHT | Ca. 3 900 g/m² |
| PILE WEIGHT<br>POIDS DU VELOURS<br>POLEINSATZGEWICHT<br>POOLGEWICHT | Ca. 770 g/m² |
| PILE ABOVE BACKING<br>POIDS DE VELOURS UTILE<br>POLNUTZSCHICHTGEWICHT<br>NUTTIG POOLGEWICHT | Ca. 500 g/m² |
| TOTAL HEIGHT<br>EPAISSEUR TOTALE<br>GESAMTDICKE<br>TOTALE DIKTE | Ca. 8.9 mm |
| PILE HEIGHT<br>EPAISSEUR DU VELOURS<br>POLDICKE<br>POOLHOOGTE | Ca. 3.5 mm |
| PILE DENSITY<br>DENSITÉ DU VELOURS<br>POLROHDICHTE<br>POOLDICHTHEID | Ca. 0.143 g/cm³ |
| TUFT DENSITY<br>NOMBRE DE TOUFFES<br>NOPPENZAHL<br>AANTAL PUNTEN | Ca. 230 000 /m² |
| CLASSIFICATION<br>CLASSEMENT<br>KLASSIFIKATION<br>CLASSIFICATIE | EN 1307<br>33- LC2 |
| CASTOR CHAIR SUITABILITY<br>EMPLOI CHAISE À ROULETTES<br>STUHLROLLENEIGNUNG<br>ROLSTOELGESCHIKTHEID | EN 985<br>A : continuous use |

| | |
|---|---|
| FIRE RESISTANCE<br>COMPORTEMENT AU FEU<br>BRENNVERHALTEN<br>BRANDGEDRAG | EN 13501-1: $B_{fl}$-s1 |
| FASTNESS TO LIGHT<br>SOLIDITÉ À LA LUMIÈRE<br>LICHTECHTHEIT<br>LICHTECHTHEID | ISO 105-B02<br>≥ 7 |
| RUBBING FASTNESS<br>SOLIDITÉ AU FROTTEMENT<br>REIBECHTHEIT<br>WRIJFECHTHEID | EN ISO 105-X12<br>≥ 4 |
| COLOUR FASTNESS TO WATER<br>SOLIDITÉ À L’EAU<br>WASSERECHTHEIT<br>WATERECHTHEID | EN ISO 105-E01<br>≥ 4 |
| THERMAL RESISTANCE<br>RÉSISTANCE THERMIQUE<br>WÄRMEDURCHLABWIDERSTAND<br>WARMTEDOORLAATWEERSTAND | ISO 8302<br>0.13 m² K/W |
| IMPACT NOISE RATING<br>ISOLATION PHONIQUE<br>TRITTSCHALLVERBESSERUNGMAB<br>GELUIDSISOLATIE | ISO 10140<br>$\Delta L_w$: 30 dB |
| SOUND ABSORPTION<br>ABSORPTION PHONIQUE<br>SCHALLABSORPTIONSGRAD<br>GELUIDSABSORPTIE | ISO 354<br>$\alpha_w$: 0.30 |
| PERMANENT ANTISTATIC<br>ANTISTATIQUE PERMANENT<br>PERMANENT ANTISTATISCH<br>PERMANENT ANTISTATISCH | ISO 6356<br>≤ 2 kV |
| TRANSVERSAL RESISTANCE<br>RÉSISTANCE TRANSVERSALE<br>DURCHGANGSWIDERSTAND<br>DOORGANGSWEERSTAND | ISO/DIS 10965<br>≤ $10^{11}$ Ohm |
| SIZE & PACKING<br>DIMENSION & EMBALLAGE<br>ABMESSUNG & VERPACKUNG<br>AFMETINGEN & VERPAKKING | 50 cm x 50 cm<br>box: 4 m²<br>pallet: 20 boxes |
| NUMBER OF COLOURS<br>NOMBRE DE COLORIS<br>ANZAHL DER FARBEN<br>AANTAL KLEUREN | 9 |
| DIMENSIONAL STABILITY<br>STABILITÉ DIMENSIONNELLE<br>DIMENSIONSTABILITÄT<br>DIMENSIONELE STABILITEIT | EN 986<br>max. 0.2 % |
| GUT-NR | C3FE11E1 |
| LEED® | Product contributes toward satisfying Credit 4.3 under LEED® |
| DGNB | modulyss is member of DGNB, the German Sustainable Building Council |





modulyss®
Zevensterrestraat 21
B 9240 Zele
T +32 (0)52 80 80 80
F +32 (0)52 80 82 00
info@modulyss.com
www.modulyss.com

We reserve all rights for technical improvements | Technische wijzigingen, ter verbetering van het product, worden voorbehouden | Sous réserve de toute modification technique visant à l’amélioration constante de nos produits | Durch technische Weiterentwicklung sind Änderungen vorbehalten

Products are not reviewed under LEED®. LEED® credit requirements cover the performance of materials in aggregate, not the performance of individual products or brands. The LEED® system has many variables in its nationally accepted benchmark for the design, construction, and operation of green buildings. For more information on LEED®, visit www.leed-rug.org/contact.